



Test Report

No.SDHL250701280101FT

Date: Jul 28, 2025

Page 1 of 3

TOUCH CABINETS HARDWARE INC.
9087 ARROW ROUTE, SUITE 110, RANCHO CUCAMONGA, CA 91730 USA

Sample Description : TOUCH T-X SOFT CLOSE CABINET HINGE
Item No. : TCH-11400 T-X
Manufacturer : TOUCH CABINETS HARDWARE INC.
Country of Origin : CHINA
Country of Destination : UNITED STATES

As above test item and its relevant information regarding to the submission are provided and confirmed by the applicant. SGS is not liable to either the test item or its relevant information, in terms of the accuracy, suitability, reliability or/and integrity accordingly.

Sample Receiving Date : Jul 19, 2025
Test Performing Date : Jul 22, 2025 to Jul 28, 2025
Test Performed : Selected test(s) as requested by applicant

Test Result Summary

No.	Test(s) Requested	Result(s)	Comments
1	ISO 9227:2022/Amd.1:2024	Grade 10	/
For further details, please refer to the following page(s)			

Signed for and on behalf of
SGS-CSTC Standards Technical Services Co., Ltd. Shunde Branch

Marco Leung

Marco Leung
Authorized Signatory

Scan to see the report



SDHL250701280101FT
Verification
check.sgsonline.com.cn



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com
1-2/F., Building 1, European Industrial Park, No.1, Shunhe South Road, Wusha, Daliang, Shunde District, Foshan, Guangdong, China 528300 t (86-757)22805888 www.ssgsgroup.com.cn
中国·广东·佛山市顺德区大良街道办事处五沙社区居民委员会顺和南路1号欧洲工业园一号厂房首层、二层 邮编: 528300 t (86-757)22805888 sgs.china@sgs.com

Member of the SGS Group (SGS SA)

TESTS AND RESULTS
Test Conducted:

ISO 9227:2022/Amd.1:2024 Corrosion Tests in Artificial Atmospheres — Salt Spray Tests.

No. of Sample:

1 piece (Sample #1). For more sample information and pictures, please refer to the following page.

1. General Information:

Test Method: Neutral Salt Spray

- Concentration of NaCl Solution: 50 g/l \pm 5 g/l
- pH of Salt Solution: 6.5~7.2
- Measure of the salt fog fall: (1.5 \pm 0.5)ml/(80cm²•h)
- Test Duration: 48 hours
- Test Temperature: (35 \pm 2) °C

2. Observation Rating (Evaluating based on ISO 10289:1999)

	Rating (R _P or R _A)	Area of defects A (%)
1. The observation rating is based on ISO 10289:1999 which is just method standard. Pass and Fail criteria will depend on buyer's acceptable specifications. 2. The observation rating is based on the 11-step scale of 0 to 10, where 0 is bad and 10 is good.	10	No defects
	9	0 < A \leq 0.1
	8	0.1 < A \leq 0.25
	7	0.25 < A \leq 0.5
	6	0.5 < A \leq 1.0
	5	1.0 < A \leq 2.5
	4	2.5 < A \leq 5.0
	3	5.0 < A \leq 10
	2	10 < A \leq 25
	1	25 < A \leq 50
	0	50 < A

3. Test Results


Specimen No.	Appearance Rating
# 1	Grade 10

Remark:


1. For the sample pictures, please refer to the following page.



Pictures of Salt Spray Tests



Before the test - View 1



After the test - View 2

End of Report